



GRASSIT FOOTBALL PRO 50

PRZEZNACZENIE	SPORT
METODA PRODUKCJI	TURFOWANA
WŁÓKNO SKŁAD SUROWCOWY	PE DTEX PE 10000
WYSOKOŚĆ RUNA	±50 MM
WYSOKOŚĆ CAŁKOWITA	±52 MM
GRAMATURA RUNA WAGA WŁÓKNA	± 1100 GR/M ²
GRAMATURA CAŁKOWITA WAGA CAŁKOWITA (Z PODKŁADEM)	± 2080 GR/M ²
ROZSTAW IGIEŁ ODLEGŁOŚĆ MIĘDZY RZĘDAMI SZWÓW	5/8"
LICZBA ŚCIEGÓW (10 CM) LICZBA ŚCIEGÓW NA 10 CM BIEŻĄCYCH	± 16 /10CM
LICZBA ŚCIEGÓW (M ²) LICZBA ŚCIEGÓW NA M²	± 10080 /M ²
PODKŁAD PIERWOTNY PIERWSZA WARSTWA NOŚNA	PP + FLEECE + NET ±180 GR/M ²
PODKŁAD WTÓRNY WARSTWA WYKOŃCZENIOWA/USZTYWNIAJĄCA	LATEX ±800 GR/M ²
PRZEPUSZCZALNOŚĆ WODY	>2000 MM/H
STABILNOŚĆ UV ODPORNOŚĆ NA PROMIENIOWANIE SŁONECZNE	UVB 3000H
TRWAŁOŚĆ KOLORU	GREY SCALE 4-5
ODPORNOŚĆ NA CHLOR	GRADE 4 (ISO 105-E03-2010)
CERTYFIKAT BEZPIECZEŃSTWA POŻAROWEGO	EFL EN 13501-1:2018
SZEROKOŚĆ ROLKI	2M / 4M
DŁUGOŚĆ ROLKI	±44 M
GWARANCJA UV	EUROPA: 5 LAT
GWARANCJA	5 LAT



All data are subject to typing errors and modifications based on technical improvements or company-internal developments. Europe Grass reserves the right to alter technical specifications due to variations in raw materials and production circumstances. All figures are average values and can vary slightly from different production runs. Roll widths are subject to contain minor differences. Only use rolls of the same batch.

Grassit

Kazimierza Wielkiego 47 A

32-400 Myślenice, Polska

REGON: 522476299

NIP: 6812093897

+48 515 401 178

biuro@grassit.pl