



GRASSIT GOLF CLUB 27

PRZEZNACZENIE	SPORT
METODA PRODUKCJI	TURFOWANA
WŁÓKNO SKŁAD SUROWCOWY	PE DTEX PE 9000
WYSOKOŚĆ RUNA	±25 MM
WYSOKOŚĆ CAŁKOWITA	±27 MM
GRAMATURA RUNA WAGA WŁÓKNA	± 3960 GR/M ²
GRAMATURA CAŁKOWITA WAGA CAŁKOWITA (Z PODKŁADEM)	± 5208 GR/M ²
ROZSTAW IGIEŁ ODLEGŁOŚĆ MIĘDZY RZĘDAMI SZWÓW	3/16"
LICZBA ŚCIEGÓW (10 CM) LICZBA ŚCIEGÓW NA 10 CM BIEŻĄCYCH	± 30 /10CM
LICZBA ŚCIEGÓW (M ²) LICZBA ŚCIEGÓW NA M²	± 63000 /M ²
PODKŁAD PIERWOTNY PIERWSZA WARSTWA NOŚNA	PP ±260 GR/M ²
PODKŁAD WTÓRNY WARSTWA WYKOŃCZENIOWA/USZTYWNIAJĄCA	LATEX ±988 GR/M ²
PRZEPUSZCZALNOŚĆ WODY	60
STABILNOŚĆ UV ODPORNOŚĆ NA PROMOENIOWNIE SŁONECZNE	DIN 53387
TRWAŁOŚĆ KOLORU	
ODPORNOŚĆ NA CHLOR	
CERTYFIKAT BEZPIECZEŃSTWA POŻAROWEGO	EFL EN 13501-1:2018
SZEROKOŚĆ ROLKI	2M / 4M
DŁUGOŚĆ ROLKI	±20 M
GWARANCJA UV	EUROPA PÓŁNOCNA: 7 LAT EUROPA POŁUDNIOWA: 5 LAT
GWARANCJA	5 LAT



All data are subject to typing errors and modifications based on technical improvements or company-internal developments. Europe Grass reserves the right to alter technical specifications due to variations in raw materials and production circumstances. All figures are average values and can vary slightly from different production runs. Roll widths are subject to contain minor differences. Only use rolls of the same batch.

Grassit

Kazimierza Wielkiego 47 A

32-400 Myślenice, Polska

REGON: 522476299

NIP: 6812093897

+48 515 401 178

biuro@grassit.pl